



Zinc-It® Instant Cold Galvanize, 13 Wt Oz No. 05048 | Item# 1003659 | Case# 1003658

Product Description High Performance coating of >93% pure zinc that actively

fights rust and corrosion. Provides protection of hot dip

galvanize with on the job convenience.

Applications Threads, exposed edges, fasteners, conduit, strapping,

welds, fencing, railings, grates, electrical poles, breaker panel housings, rain spouts, signs, doors, trailers, waste

containers, catwalks, and guard rails.

Unit Package Description 16 Ounce Aerosol

Brand CRC

Generic Description 1 Instant Cold Galvanized Coating

Net Fill 13 Wt Oz

UPC Code 078254050485

Unit Dimensions 7.75H x 2.63W x 2.63D in

Units Per Case 12

Case Dimensions 8.25H x 8.38W x 11D in

Cases Per Pallet 75
Case Weight 15 lbs

I 2 of 5 Code 30078254050486

Appearance Gray Viscous Liquid

Flash point (F) -2.2°F Flash point (C) -19°C

Flammability Class - CPSC Extremely Flammable

Spec Gravity Concentrate 0.77 to 0.85

Plastic Safe Yes

Evaporation Rate >1 (butyl acetate=1)

Dry Time - Fully Dry 8 Hours
Dry Time - Tack Free 20 Minutes

Recoat Before 1 Hour or After 48 Hours

Coverage 28 to 32 Sq Ft at 3 Mil Dry

Working Temp (F) 130°F (Continuous) / 150°F (Intermittent)

Last revised: 7/23/2019

Page 1 of 2







Working Temp (C) 54.4°C (Continuous) / 65.6°C (Intermittent)

Propellant Hydrocarbon

Aerosol Flammability Level III

Military Specification Meets requirements of Mil-P-26915, Meets requirements of Mil-P-46105

DOT Proper Shipping Name Aerosols, Flammable, Limited Quantity (Marine Pollutant)

VOC % (Consumer Product 45.6

def)

VOC g/L (Consumer 555.6

Product def)

VOC lbs/gal (Consumer 4.64

Prod def)

VOC Category Aerosol Coating: Metallic

MIR Limit (EPA) 1.9 MIR Limit (CA) 1.25

MIR Value 1.17

Removal (How To) Remove with aromatic solvents, Xylene. Toluene can be

used, but is not recommended.

Last revised: 7/23/2019

Page 2 of 2

